Thermal evolution of structure and photocatalytic activity in polymer microsphere templated TiO₂ microbowls[☆]

Deniz Altunoz Erdogan^a, Meryem Polat^a, Ruslan Garifullin^b,
Mustafa O. Guler^b, Emrah Ozensoy^{a,*},¹

^a Department of Chemistry, Bilkent University, 06800 Ankara, Turkey

^b Institute of Materials Science and Nanotechnology, National Nanotechnology Research Center (UNAM), Bilkent University, 06800 Ankara, Turkey

ARTICLE INFO

Article history:

Received 22 January 2014

Received in revised form 4 April 2014

Accepted 12 April 2014

Available online 21 April 2014

Keywords:

TiO₂

Photocatalyst

Cross-linked divinyl benzene

NO(g) oxidation

Rhodamine B

ABSTRACT

Polystyrene cross-linked divinyl benzene (PS-co-DVB) microspheres were used as an organic template in order to synthesize photocatalytic TiO₂ microspheres and microbowls. Photocatalytic activity of the microbowl surfaces were demonstrated both in the gas phase via photocatalytic NO(g) oxidation by O₂(g) as well as in the liquid phase via Rhodamine B degradation. Thermal degradation mechanism of the polymer template and its direct influence on the TiO₂ crystal structure, surface morphology, composition, specific surface area and the gas/liquid phase photocatalytic activity data were discussed in detail. With increasing calcination temperatures, spherical polymer template first undergoes a glass transition, covering the TiO₂ film, followed by the complete decomposition of the organic template to yield TiO₂ exposed microbowl structures. TiO₂ microbowl systems calcined at 600 °C yielded the highest per-site basis photocatalytic activity. Crystallographic and electronic properties of the TiO₂ microsphere surfaces as well as their surface area play a crucial role in their ultimate photocatalytic activity. It was demonstrated that the polymer microsphere templated TiO₂ photocatalysts presented in the current work offer a promising and a versatile synthetic platform for photocatalytic DeNO_x applications for air purification technologies.

© 2014 Elsevier B.V. All rights reserved.

1. Introduction

Shape-defined nano and micro scale titanium dioxide (TiO₂) structures are widely utilized as photocatalytic systems; where they have attracted a particular interest in environmental applications. It has been reported that controlling particle shape, geometry, size, surface morphology, electronic structure, relative abundance of anatase/rutile surface domains and the nature of the surface functional groups (such as –OH) are some of the key factors for designing efficient TiO₂ photocatalytic architectures [1–5].

TiO₂ materials can be produced with unique morphologies, shapes and structures at the micro/nanoscale revealing extraordinary physical, chemical, electronic and optical properties, rendering these systems very versatile photocatalysts [3]. Template directed synthesis is one of the approaches for fine-tuning size,

shape and porosity of TiO₂ particles [6–8]. In particular, utilization of organic templates such as polymers offers vast opportunities for controlling the shapes of inorganic materials at the micrometer/nanometer scale. Such strategies can be exploited to synthesize shape-defined TiO₂ materials exhibiting nano/micro spheres [9], hollow structures [10], tubes [11], wires [3], core-shell structures [3], and egg-yolk structures [12].

In the current report, TiO₂ microbowls were synthesized by using polystyrene crosslinked divinyl benzene (PS-co-DVB) microspheres. The polymer template was removed by calcination and TiO₂ microbowls were produced. The effect of the calcination temperature on the structural properties and activity of the photocatalysts were studied in the gas phase as well as in the solution phase oxidation reactions.

2. Experimental

2.1. Sample preparation

A custom sol–gel method combined with a polymer templating technique was used for the synthesis of TiO₂ microbowl structures

[☆] Electronic Supplementary Information (ESI) available: Gas-phase and solution-phase photocatalytic performance of P25.

* Corresponding author. Tel.: +90 312 290 2121; fax: +90 312 266 4068.

E-mail address: ozensoy@fen.bilkent.edu.tr (E. Ozensoy).

¹ Web: <http://www.fen.bilkent.edu.tr/~ozensoy>.

Scheme 1. Synthetic protocol for PS-co-DVB-templated TiO_2 microspheres and microbowls.

[13–15]. Commercially available polystyrene cross-linked divinyl benzene (PS-co-DVB) microspheres (Aldrich) with an average particle size of ca. 8 μm were used as the template material. Preparation of TiO_2 microspheres and microbowls is shown in Scheme 1. First, equal masses (i.e. 1.0 g) of polymer microspheres and titanium(IV) isopropoxide (TIP, 97%, Aldrich) were mixed and stirred for 24 h under ambient conditions. Then, 100 mL of deionized water (Milli-Q, 18.2 $\text{M}\Omega\text{ cm}$) was added to the mixture under continuous stirring (24 h), where hydrolysis and condensation reactions were carried out. Then, microspheres were vacuum-filtered, washed with deionized water and dried for 24 h at 60 °C in air. Later, the sample was calcined in air in order to remove the polymer template as well as to crystallize the inorganic component (i.e. TiO_2). Samples were calcined at various temperatures (200, 300, 400, 500, 600, 700 °C) in air for 2 h (using a heating rate of 8 °C/min) to control crystallinity and surface morphology of TiO_2 microspheres. Synthesized samples were named as PsTi-200, PsTi-300, PsTi-400, PsTi-500, PsTi-600, and PsTi-700 depending on the calcination temperature.

2.2. Structural characterization

The morphology and the particle size of the polymer templated TiO_2 microspheres and microbowls were investigated by using a Carl-Zeiss Evo40 environmental scanning electron microscope (SEM) equipped with a Bruker energy dispersive X-Ray (EDX) detector. Determination of the crystal structure of the synthesized materials were carried out with a Rigaku Miniflex X-ray diffractometer (XRD) equipped with $\text{Cu K}\alpha$ radiation operated at 30 kV, 1.54 Å and 15 mA. The XRD patterns were recorded in the 2θ range of 10–60° with a step width of 0.02 s^{−1}. Raman spectra of the samples were collected in the range of 200–1500 cm^{-1} with a resolution of 4 cm^{-1} using a Horiba Jobin Yvon LabRAM HR800 spectrometer equipped with a confocal Raman BX41 microscope. The Raman spectrometer was equipped with a Nd:YAG laser ($\lambda = 532.1\text{ nm}$) where the laser power was 20 mW. The thermal properties of the TiO_2 systems were also investigated by using thermogravimetric analysis (TGA). TGA measurements were carried out between 30 and 800 °C (at a heating rate of 10 °C/min and under nitrogen flow) by using a TA Instruments TGA-Q500 setup. The specific surface area (SSA) of the TiO_2 samples was determined by

conventional Brunauer–Emmett–Teller (BET) N_2 adsorption method with a Micromeritics Tristar 3000 surface area and pore size analyzer. Prior to the BET measurements, all of the samples were out gassed in vacuum for 2 h at 150 °C.

2.3. Photocatalytic performance analysis measurements

2.3.1. Gas-phase photocatalytic oxidation performance measurements

Reactivity of the TiO_2 microstructures was studied via photocatalytic NO oxidation ($\text{NO(g)} + \frac{1}{2} \text{O}_2(\text{g}) \rightarrow \text{NO}_2(\text{g})$). The gas phase photocatalytic activity of the TiO_2 microstructures was analyzed in a custom-made continuous flow reaction system, which is shown in Scheme 2. The experimental setup was comprised of a high-purity gas mixture containing NO(g) (100 ppm NO(g) in $\text{N}_2(\text{g})$, Linde GmbH), $\text{O}_2(\text{g})$ (99.998%, Linde GmbH) and $\text{N}_2(\text{g})$ (99.998%, Linde GmbH) which was humidified with 70% RH (relative humidity, measured via a Hanna HI 9565 humidity analyzer at the sample position in the photocatalytic reactor). In a typical gas phase photocatalytic performance analysis test, a total gas flow rate of 1 SLM (SLM, standard liters per minute) was used, where the volumetric flow rates of $\text{N}_2(\text{g})$, $\text{O}_2(\text{g})$ and NO(g) were set to be 0.750 SLM, 0.250 SLM and 0.010 SLM via mass flow controllers (MFCs, MKS, 1479A), respectively. Before the performance tests, synthesized TiO_2 microsphere/microbowl powder samples were dispersed on a poly-methyl methacrylate (PMMA) sample holder ($2 \times 40 \times 40\text{ mm}^3$) and irradiated with UVA illumination (Sylvania UV-lamp, black-light, F8W, T5, 368 nm) under ambient conditions for 18 h in order to remove the surface contaminations and to activate the photocatalysts. After this activation and decontamination procedure, samples were inserted into the photocatalytic flow reactor for performance analysis. UVA illumination source used in the performance analysis tests (Sylvania UV-lamp, black-light, F8W, T5, 368 nm) generated a UVA photon flux of 7.5 W/m^2 at the sample position under typical reaction conditions. During the performance tests, reaction gases were swept over a 950 mg photocatalyst sample and the concentration of NO(g) , $\text{NO}_2(\text{g})$ and total $\text{NO}_x(\text{g})$ species in the photocatalytic reactor were quantitatively measured online with a Horiba APNA-370 chemiluminescence NO_x analyzer.

Scheme 2. Gas-phase photocatalytic performance analysis setup.

Gas phase photocatalytic activity measurements are reported in terms of percent photonic efficiencies ($\zeta\%$) as described in Eqs. (1) and (2).

$$\zeta\% = \frac{n_{\text{NO}_x}}{n_{\text{photon}}} \times 100 \quad (1)$$

where n_{NO_x} corresponds to either the decrease in the total number of moles of all gaseous NO_x species or the number of moles of $\text{NO}_2(\text{g})$ generated in a 60 min (i.e. 3600 s) photocatalytic performance test. On the other hand, n_{photon} corresponds to the total number of moles of incident UVA photons impinging on the catalyst surface in 3600 s, which can be calculated through Eq (2) as:

$$n_{\text{photon}} = \frac{(I \lambda S t)}{(N h c)} \quad (2)$$

where I represents the photon power density of the UVA lamp, experimentally measured at the sample position in the photocatalytic reactor (typically, 7.5 W/m^2), λ is the representative emission wavelength of the UVA lamp (i.e. 368 nm), S is the surface area of the photocatalyst sample holder in the reactor that is exposed to the UVA irradiation (i.e. $4 \text{ cm} \times 4 \text{ cm} = 16 \text{ cm}^2$); t is the duration of the performance test (i.e. 3600 s), N is the Avogadro's number, h is Planck's constant and c is the speed of light.

2.3.2. Liquid-phase photocatalytic oxidation performance measurements

Liquid-phase photocatalytic oxidation activity of the TiO_2 microstructures was demonstrated by photodegradation [16–18]. Oxidative degradation of Sulforhodamine B (RhB, 95%, Sigma) under UVA irradiation (Sylvania UV-lamp, F8W, T5, Black-light, 8 W, 368 nm) was conducted in a batch-mode photocatalytic reactor of dimensions $45 \times 23 \times 28 \text{ cm}^3$. An aqueous RhB solution at concentration of 1 mg/L and 30 mg of TiO_2 microstructures was added into the reactor and stirred continuously at a stirring rate of 100 rpm. Then, the photocatalytic degradation process was studied by measuring the change in the dye concentration with an UV–vis spectrophotometer (Carry 300, Agilent). Attenuation of the major absorption band of RhB (564 nm) associated with the $S_0 \rightarrow S_1$ absorption [19] was recorded every 30 min until the test solution became visually transparent. Before the UV–vis absorption measurements, test solutions were centrifuged and the absorbance of the filtrate was recorded. By using a calibration curve ($R^2 = 9994$) of the dye solution, the percent decolorization efficiency (D_{ef}) of the system at an irradiation time t (min) was calculated as described in Eq. (3) [20].

$$D_{\text{ef}}(\%) = \frac{(C_0 - C_t)}{C_0} \times 100 \quad (3)$$

In Eq. (3), C_0 and C_t represent the concentration of the test solution before and after irradiation at time t , respectively. A plot of C_0/C versus irradiation time (t) determines the decolorization degree of the test solution.

3. Results and discussion

3.1. Structural characterization of polymer-templated TiO_2 microstructures

The SEM images in Fig. 1a–d illustrate the morphology and the particle size of the TiO_2 coated PS-co-DVB microspheres. The particle size variation in the microstructures stems from the corresponding size distribution in the nascent commercial PS-co-DVB material. SEM images in Fig. 1a–d and the corresponding EDX measurements (Fig. 1e) of the TiO_2 -coated microspheres revealed that the surface of the polymer microspheres was coated with a thin layer of TiO_2 and additional TiO_2 was also further deposited.

Fig. 1. (a–d) SEM images and (e) a representative EDX spectrum of TiO_2 -coated PS-co-DVB microspheres before calcination.

Upon calcination of the TiO_2 coated PS-co-DVB microspheres between 200 and 700°C , significant morphological changes were observed. The microspheres were converted into microbowls (Fig. 2). This observation was also accompanied by a considerable weight loss, which will be discussed further in the text (Fig. 3). Fig. 2 shows the SEM images and the corresponding EDX spectrum of the polymer-templated TiO_2 microbowls, which were calcined at 600°C at ambient conditions for 2 h. Due to decomposition of the polymer template and the associated formation of $\text{H}_x\text{C}_y(\text{g})$ and $\text{H}_x\text{C}_y\text{O}_2(\text{g})$, pressure accumulation inside the microsphere leads to the rupture of the spherical morphology during the evolution of the entrapped gas. The resulting open microbowl structures are shown in the inset of Fig. 2b. The interior cavities of the microbowls have an average diameter of $8 \mu\text{m}$ with an average wall thickness of 600 nm . The EDX spectrum of the microbowls (Fig. 2b) indicates $\text{TiO}_2/\text{TiO}_x$ content with a relatively minor contribution of carbon-based species. On the other hand, EDX spectrum of the same samples before the calcination revealed excessive C signal (Fig. 1e).

Evolution of $\text{H}_x\text{C}_y(\text{g})$ and $\text{H}_x\text{C}_y\text{O}_2(\text{g})$ and the anticipated weight loss of the sample upon the decomposition/degradation of the polymer template below 600°C is in perfect agreement with the TGA results shown in Fig. 3, which show a sharp gravimetric loss

Fig. 2. (a) SEM image, (b) EDX spectrum of PS-co-DVB templated TiO₂ microbowls after calcination at 600 °C for 2 h (inset shows the detailed morphology of the microbowls in SEM).

within 400–500 °C. The TGA curve of TiO₂-coated PS-co-DVB microspheres (Fig. 3) exhibits a 2.7 wt% loss in the temperature range of 30–250 °C due to the evaporation of water and other volatile organics. TiO₂ reveals a negligible gravimetric loss within 30–800 °C, while pure/uncoated polystyrene undergoes almost 100 wt% loss within 300–500 °C due to decomposition/degradation [21–23].

Fig. 3. TGA measurement for PS-co-DVB templated TiO₂ microspheres.

Thus, TGA data in Fig. 3, suggest that after the 71 wt% loss at $T > 400$ °C, a large portion of the remaining sample, which corresponds to 29% of the original sample weight, is due to the inorganic content (i.e. TiO₂).

In order to investigate the influence of the calcination temperature on the photocatalyst structure and the photocatalytic activity, samples were calcined at different temperatures within 200–700 °C. Corresponding XRD patterns and Raman spectra of these samples are presented in Fig. 4. Calcination at 200 and 300 °C leads to the formation of an amorphous TiO₂/TiO_x structure, which starts to crystallize into a rather disordered anatase phase at 400 °C with a small average particle size, evident from the corresponding broad anatase XRD diffraction signals (ICDD Card No: 21-1272) in Fig. 4a and the characteristically intense anatase Raman scattering observed at 144 cm⁻¹ [24–26]. At 500 °C, a well-ordered anatase phase with a larger average particle size is formed as can be seen from the sharp and intense anatase signals in both XRD (Fig. 4a) and Raman (Fig. 4b) results. At this temperature, rutile phase also appears as a secondary phase in both XRD results shown in Fig. 4a (ICDD card no: 04-0551) as well as in the Raman data in Fig. 4b. Formation of the rutile phase leads to the evolution of typical Raman scattering features at 236, 447, 612, 826 cm⁻¹ [24–26]. Rutile phase becomes more crystalline and abundant at higher calcination temperatures. Upon calcination at 700 °C, rutile becomes the dominant phase, although anatase phase can still be detected as a secondary phase (Fig. 4a and b).

3.2. Photocatalytic activity of the polymer-templated TiO₂ microspheres and microbowls

3.2.1. Gas-phase photocatalytic oxidation performance

The photocatalytic NO(g) oxidation with O₂(g) was used as a model reaction [27–32]. Fig. 5 illustrates a typical gas phase photocatalytic performance analysis test in which the photocatalyst sample is exposed to a feed gas mixture containing 1 ppm NO(g) as well as a certain composition of N₂(g) and O₂(g) with a 70% RH (see Section 2 for details). Fig. 5 shows the time-dependent profiles for the total NO_x concentration (i.e. sum of the concentrations of all of the NO_x species existing in the reactor, i.e. blue curve in Fig. 5) as well as separate NO(g) (black curve) and NO₂(g) (red curve) concentrations in the photocatalytic reactor measured by the chemiluminescence NO_x analyzer. As shown in Fig. 5, during the initial 15 min of the performance test, gas mixture containing 1 ppm NO(g) is fed to the photocatalyst while UVA lamp is in off position and the reactor is kept in dark in order to prevent any exposure to sunlight. This leads to a minor transient fall in the total NO_x(g) and NO(g) concentrations, which is associated with the dilution of the gas in the reactor pipeline and the thermal adsorption of NO_x species on the gas lines, reactor walls as well as on the photocatalyst surface. As the system is kept in dark under these conditions, no photocatalytic activity is observed during this initial stage, which is evident by the lack of any NO₂(g) production. After the initial transient period, reactor walls and the photocatalyst surface are saturated with NO_x, after which NO_x(g) and NO(g) traces quickly return to the original inlet concentration value of 1 ppm.

Next, UVA lamp is turned on and the photocatalytic reaction is started. Upon UVA radiation, a sharp and a permanent fall in the NO(g) and total NO_x(g) concentrations along with a quick rise in NO₂(g) signal, were observed. This is caused by conversion of NO(g) into NO₂(g) via photocatalytic oxidation. In addition, generated NO₂(g) can also adsorb on the photocatalyst surface in the form of chemisorbed NO₂, nitric/nitrous acid, nitrites and nitrates [24–26,33] and stored in the solid state, leading to a further decrease in the NO(g) signal. Furthermore, direct photocatalytic decomposition and photo-reduction of NO(g) forming N₂(g)

Fig. 4. (a) XRD patterns, (b) Raman spectra of PS-co-DVB templated TiO₂ microspheres/microbowls upon calcination at 200 °C, 300 °C, 400 °C, 500 °C, 600 °C, and 700 °C for 2 h under ambient conditions (inset highlights the detailed Raman features of PsTi-600 and PsTi-700 samples). A: anatase, R: rutile.

and/or N₂O(g) cannot be ruled out [34]. The total NO_x concentration (blue curve (which is mostly comprised of the sum of NO(g) and NO₂(g) signals) in Fig. 5 stays always below 1 ppm during the UVA-activated regime, illustrating the continuous photocatalytic activity.

Gas-phase photocatalytic performance tests similar to the one given in Fig. 5 were also performed on other PS-co-DVB templated TiO₂ microsphere/microbowl photocatalysts, which were calcined at various temperatures between 200 and 700 °C. Percent photonic efficiency values derived from such experiments are shown in Fig. 6, where blue bars represent the % photonic efficiency of total NO_x(g) decrease, while red bars correspond to the % photonic efficiency of NO₂(g) production.

Fig. 6 shows that PsTi-200 sample reveals both considerable NO_x storage (blue bar) and NO₂(g) production (red bar) capabilities.

Fig. 5. Typical time-dependent concentration profiles for total NO_x(g), NO(g) and NO₂(g) over PS-co-DVB templated TiO₂ microbowl photocatalyst (PsTi-600) during gas-phase photocatalytic NO oxidation activity tests. (For interpretation of the references to color in this figure legend, the reader is referred to the web version of this article.)

On the other hand, upon increasing the calcination temperature to 300 °C, both NO_x storage and NO₂(g) production performances were observed to decline drastically. On the other hand, after calcination at 400 °C, NO_x storage capability is recovered while NO₂(g) production is still noticeably suppressed. Above 500 °C, although NO_x storage capacity decreases to a certain extent, NO₂(g) production capability is fully regained, reaching its highest value at 600 °C. Increasing the calcination temperature to 700 °C leads to a decrease in the NO_x storage and NO₂(g) production performances simultaneously.

Interesting gas-phase photocatalytic performance trends given in Fig. 6 can be elucidated by using the structural properties of the polymer-templated TiO₂ microstructures shown in Scheme 3. The crosslinked polystyrene systems have typical glass transition temperatures (*T_g*) within 100–150 °C, above which the solid polymer tends to switch to a mobile molten/glassy state [23]. As can be seen from the specific surface area (SSA) results shown in Scheme 3, PsTi-200 sample has a moderately high SSA (86 m²/g) suggesting that the mobilized PS-co-DVB microsphere template starts to segregate on the very top surface, only partially covering/blocking

Fig. 6. Comparison of the photonic efficiencies of TiO₂ microspheres/microbowls. (For interpretation of the references to color in this figure legend, the reader is referred to the web version of this article.)

Scheme 3. Temperature-induced structural evolution of TiO₂ microspheres/microbowls.

the amorphous TiO₂/TiO_x coating on the microsphere system. Thus, at this calcination temperature, TiO₂/TiO_x coating is still partially accessible for gas phase photocatalytic NO_x storage and NO₂(g) production (Fig. 6).

However, upon calcination at 300 °C, the SSA was observed to decrease by about 50%, which is accompanied by a total loss of photocatalytic NO_x storage and NO₂(g) production activities (Fig. 6). Apparently, calcination at 300 °C leads to the segregation of the mobilized PS-co-DVB microsphere template onto the TiO₂/TiO_x coating (Scheme 3). Hence, access to the photocatalytic active sites to NO(g) is completely blocked and the photocatalytic activity is entirely lost.

Increasing the calcination temperature to 400 °C shows a unique switch in the photocatalytic activity. This is the borderline temperature, where the PS-co-DVB template starts to decompose leading to the rupture of the microspheres and formation of the microbowls. Formation of microbowls and elimination of the carbonaceous/polymeric film at 400 °C is also fully consistent with the drastic increase in the SSA of the system to 159 m²/g (Scheme 3). The increase in the SSA is also accompanied by the formation of a cavity inside the microspheres due to the degradation of the PS-co-DVB template, generating additional adsorption sites. At this temperature, Ti-coating reveals mostly an amorphous/porous nature, which also exhibits poorly crystalline anatase domains (Fig. 4). Thus, due to the decomposition/removal of the polymer template, most of the photocatalytic active sites on the amorphous Ti-coating become readily accessible and photocatalytic NO oxidation can be performed efficiently which is evident by the recovery of the photocatalytic NO_x storage (blue bar for PsTi-400 in Fig. 6). Although PsTi-400 sample can efficiently perform photocatalytic NO_x storage, yet it generates a relatively small amount of NO₂(g). This could be due to the large SSA of the PsTi-400 sample with a large number of adsorption sites that can immediately capture

NO₂(g) in the form of nitrites and nitrates on the TiO₂ surface and prevent NO₂(g) slip into the gas phase.

Fig. 6 shows that as the calcination temperature is increased from 400 °C to 500 °C, the photocatalytic NO_x storage decreases significantly in contrast to the noticeable increase in the NO₂(g) production. Within 400–500 °C, PsTi samples undergo a substantial crystallographic transformation (Fig. 4), where porous and amorphous TiO₂ domains crystallize into ordered anatase and rutile domains resulting in a significant loss in the SSA. Along these lines, PsTi-500 sample has a SSA of 13.9 m²/g (Scheme 3). Thus, the photocatalytic NO_x storage capacity falls in line with the corresponding the SSA loss, suggesting that NO₂(g) generated via photo-oxidation readily slips into the gas phase. However, this does not mean that the photocatalytic activity decreases upon increasing the temperature from 400 °C to 500 °C. By comparing the combined NO_x storage and NO₂ formation results (i.e. sum of the red and blue bars in Fig. 6) for 400 °C and 500 °C along with the corresponding SSA values suggests that PsTi-500 sample has a considerably higher *per-site basis* photocatalytic activity with respect to PsTi-400.

Fig. 6 indicates that the optimum gas-phase photocatalytic activity is reached for the PsTi-600 sample, which reveals a lower anatase/rutile ratio (Fig. 4a and Scheme 3) estimated by XRD results by using the approach developed by Spurr and Myers [35]. On the other hand, as the calcination temperature is increased to 700 °C, concomitant to the further decrease in the anatase/rutile ratio, photocatalytic activity starts to decrease. Thus, it is apparent that rather than the sole SSA values, crystallographic and electronic properties of the TiO₂ microspheres/microbowls play a major role in determining their ultimate gas-phase photocatalytic activities.

3.2.2. Solution-phase photocatalytic oxidation performance

Photocatalytic activity of TiO₂ microstructure calcined at different temperatures was also studied by conventional solution phase

Fig. 7. Time-dependent UV-Vis absorption spectra showing UVA-induced photocatalytic degradation of RhB in the presence of PS-co-DVB templated TiO₂ microbowls calcined at 600 °C for 2 h.

photocatalytic oxidation of RhB. A typical series of time-dependent UV-vis absorption spectra obtained during the UVA irradiation is presented in Fig. 7. This series of spectra corresponds to the PsTi-600 sample which is comprised of TiO₂ microbowls (Fig. 2). During the photocatalytic reaction, the characteristic RhB absorption band located at 564 nm gradually decreases indicating photocatalytic degradation/oxidation of RhB. After 330 min of UVA irradiation, the dye solution becomes visibly colorless and the 564 nm signal vanishes almost completely.

Time-dependent decolorization efficiency results for the remaining samples are summarized in Fig. 8a. The solution phase photocatalytic oxidation experiments could not be realized for the PsTi-200 and PsTi-300 samples due to low density of the corresponding solid photocatalysts (originating from their high polymer content), which results in the floating of the microspheres on the

Fig. 8. (a) Liquid-phase photocatalytic reactivity of PS-co-DVB templated TiO₂ microspheres/microbowls in Rhodamine B photodegradation via UVA irradiation, (b) photocatalyst-containing 1 mg/L RhB solutions after 18 h UVA irradiation.

aqueous medium preventing their efficient mixing and homogeneous UVA exposure. Fig. 8a shows that RhB concentration in the solution decreases monotonically with increasing irradiation time which is also illustrated in Fig. 8b (for photocatalyst-containing 1 mg/L RhB solutions after 18 h UVA irradiation). Control experiments performed by exposing 1 mg/L RhB solution to UVA in the absence of a photocatalyst (data not shown) did not lead to any decolorization under typical reaction conditions. The liquid-phase photocatalytic activity of the synthesized TiO₂ structures exhibits a strong dependence on the calcination temperature. Fig. 8a clearly indicates that PsTi-600 sample which has a microbowl structure (Fig. 2) and exhibits predominantly anatase phase (in addition to rutile as a secondary phase) reveals the highest liquid-phase photocatalytic activity. The PsTi-400 sample is significantly less active than all of the analyzed samples (Fig. 8), and is comprised of a poorly crystalline anatase phase (Fig. 4). This suggests that solution-phase photocatalytic activity requires formation of ordered anatase/rutile crystallographic phases. On the other hand, Fig. 8a also shows that the solution-phase photocatalytic activity tends to decrease at elevated calcination temperatures such as 700 °C, suggesting that a rutile-dominant TiO₂ microbowl structure is not favorable.

It is worth mentioning that the solution-phase photocatalytic reactivity trends presented in Fig. 8a cannot be explained solely based on the SSA values of the synthesized materials. Although PsTi-400 sample reveals a significantly higher SSA than all of the other synthesized materials, it has a considerably lower liquid-phase photocatalytic activity (Fig. 8). In other words, crystallographic and the electronic properties of the TiO₂-coated PS-co-DVB microspheres/microbowls seem to play a major role in their liquid-phase photocatalytic reactivity.

It is worth mentioning that we have also performed similar liquid-phase and gas-phase photocatalytic activity tests using a benchmark photocatalyst (P25) (Figs. S1 and S2, ESI†). We observed that total photocatalytic activity for P25 in both liquid and gas phase experiments were about two times higher than that of the best PS-co-DVB templated TiO₂ microsphere/microbowl photocatalyst (PsTi-600). The SSA of P25 is about 50 m²/g, which is about more than 5 times greater than that of PsTi-600. Thus, per-site basis photocatalytic activity of PsTi-600 is still 2.5 times higher than that of P25. This suggests that by optimizing the polymer microsphere templating strategy (for instance by using polymer nanospheres with smaller average particle sizes and thus higher SSA), advanced photocatalytic systems can be designed, which reveal higher photocatalytic performance both in terms of total photocatalytic activity as well as per-site-basis photocatalytic activity. In addition, further improvements in the photocatalytic performance of PS-co-DVB templated TiO₂ microsphere/microbowl photocatalysts can also be achieved by incorporating plasmonic metal nanoparticles to these systems [36]. Such experimental efforts are currently underway in our research group [37].

4. Conclusions

In this work, PS-co-DVB microsphere templated TiO₂ photocatalysts were synthesized via sol-gel method. Influence of the calcination temperature on the structural properties and the photocatalytic activity of these systems under UVA excitation were investigated both in the gas phase (by studying photocatalytic NO(g) oxidation by O₂(g)) as well as in the solution phase (by monitoring Rhodamine B photocatalytic degradation). The polymer microspheres were found to be covered with a thin film of TiO₂/TiO_x as well as TiO₂/TiO_x nanoparticles. Photocatalytic activity carried out in the solution phase and in the gas phase showed that the photocatalyst calcined at 600 °C exhibiting a microbowl structure, yielded the highest *per-site-basis* photocatalytic

activity which is even greater than that of the commercial benchmark P25. Our findings indicate that not only the specific surface area but also the crystallographic and electronic properties of the TiO₂ microstructures play a major role in determining their ultimate photocatalytic activities. This suggests that polymer-templated TiO₂ microstructures offer a promising versatile synthetic platform for photocatalytic DeNO_x applications, which can be further improved by using polymer nanosphere templates with higher SSA or by additional functionalization with transition metal nanoparticles and/or plasmonic components.

Acknowledgments

Authors gratefully acknowledge Associate Prof. Dönüş Tuncel for fruitful discussions, and Zafer Say for performing BET measurements. E.O. also acknowledges financial support from Turkish Academy of Sciences through the “TUBA-GEBIP Outstanding Young Scientist Prize” and from Fevzi Akkaya Science Fund (FABED) through Eser Tümen Scientific Achievement Award as well as the Scientific and Technical Research Council of Turkey (TUBITAK) (Project Code: 109M713).

Appendix A. Supplementary data

Supplementary material related to this article can be found, in the online version, at <http://dx.doi.org/10.1016/j.apsusc.2014.04.082>.

References

- [1] U. Diebold, The surface science of titanium dioxide, *Surf. Sci. Rep.* 48 (2003) 53–229.
- [2] T.L. Thompson, J.T. Yates, Surface science studies of the photoactivation of TiO₂—new photochemical processes, *Chem. Rev.* 106 (2006) 4428–4453.
- [3] X. Chen, S.S. Mao, Titanium dioxide nanomaterials: synthesis, properties, modifications, and applications, *Chem. Rev.* 107 (2007) 2891–2959.
- [4] A. Fujishima, X. Zhang, D.A. Tryk, TiO₂ photocatalysis and related surface phenomena, *Surf. Sci. Rep.* 63 (2008) 515–582.
- [5] M.A. Henderson, A surface science perspective on TiO₂ photocatalysis, *Surf. Sci. Rep.* 66 (2011) 185–297.
- [6] Y. Liu, J. Goebel, Y. Yin, Templated synthesis of nanostructured materials, *Chem. Soc. Rev.* 42 (2013) 2610–2653.
- [7] C.N.R. Rao, A. Govindaraj, Synthesis of inorganic nanotubes, *Adv. Mater.* 21 (2009) 4208–4233.
- [8] A.S. Attar, M.S. Ghamsari, F. Hajiesmaeilbaigi, S. Mirdamadi, K. Katagiri, K. Koumoto, Sol–gel template synthesis and characterization of aligned anatase-TiO₂ nanorod arrays with different diameter, *Mater. Chem. Phys.* 113 (2009) 856–860.
- [9] F. Cesano, D. Pellerej, D. Scarano, G. Ricchiardi, A. Zecchina, Radially organized pillars in TiO₂ and in TiO₂/C microspheres: synthesis, characterization and photocatalytic tests, *J. Photochem. Photobiol., A: Chem.* 242 (2012) 51–58.
- [10] J. Hu, M. Chen, X. Fang, L. Wu, Fabrication and application of inorganic hollow spheres, *Chem. Soc. Rev.* 40 (2011) 5472–5491.
- [11] T. Kang, A.P. Smith, B.E. Taylor, M.F. Durstock, Fabrication of highly-ordered TiO₂ nanotube arrays and their use in dye-sensitized solar cells, *Nano Lett.* 9 (2009) 601–606.
- [12] I. Lee, J.B. Joo, Y. Yin, F. Zaera, A yolk@shell nanoarchitecture for Au/TiO₂ catalysts, *Angew. Chem. Int. Ed.* 50 (2011) 10208–10211.
- [13] U. Meyer, A. Larsson, H. Hentze, R.A. Caruso, Templating of porous polymeric beads to form porous silica and titania spheres, *Adv. Mater.* 14 (2002) 1768–1772.
- [14] A.S. Deshpande, D.G. Shchukin, E. Ustinovich, M. Antonietti, R.A. Caruso, Titania and mixed titania/aluminum, gallium, or indium oxide spheres: Sol–gel/template synthesis and photocatalytic properties, *Adv. Funct. Mater.* 15 (2005) 239–245.
- [15] J.H. Schattka, D.G. Shchukin, J. Jia, M. Antonietti, R.A. Caruso, Photocatalytic activities of porous titania and titania/zirconia structures formed by using a polymer gel templating technique, *Chem. Mater.* 14 (2002) 5103–5108.
- [16] L. Yuan, S. Meng, Y. Zhou, Z. Yue, Controlled synthesis of anatase TiO₂ nanotube and nanowire arrays via AAO template-based hydrolysis, *J. Mater. Chem. A* 1 (2013) 2552–2557.
- [17] D.A.H. Hanaor, C.C. Sorrell, Review of the anatase to rutile phase transformation, *J. Mater. Sci.* 46 (2011) 855–874.
- [18] P. Zhang, C. Shao, Z. Zhang, M. Zhang, J. Mu, Z. Guo, Y. Sun, Y. Liu, Core/shell nanofibers of TiO₂@carbon embedded by Ag nanoparticles with enhanced visible photocatalytic activity, *J. Mater. Chem.* 21 (2011) 17746–17753.
- [19] N.K.M.N. Srinivas, S.V. Rao, D.N. Rao, Saturable and reverse saturable absorption of Rhodamine B in methanol and water, *J. Opt. Soc. Am. B: Opt. Phys.* 20 (2003) 2470–2479.
- [20] K. Sridharan, T.J. Park, Thorn-ball shaped TiO₂ nanostructures: Influence of Sn²⁺ doping on the morphology and enhanced visible light photocatalytic activity, *Appl. Catal., B: Environ.* 134 (2013) 174–184.
- [21] D. Yu, J.H. An, S.D. Ahn, S. Kang, K.S. Suh, Titanium dioxide/P(St-co-DVB)-MAA hybrid composite particles prepared by dispersion polymerization, *Colloid Surf., A: Physicochem. Eng. Aspects* 266 (2005) 62–67.
- [22] E.D. Mekeridis, I.A. Kartsonakis, G.S. Pappas, G.C. Kordas, Release studies of corrosion inhibitors from cerium titanium oxide nanocontainers, *J. Nanopart. Res.* 13 (2011) 541–554.
- [23] S.E. Shim, S. Yang, H.H. Choi, S. Choe, Fully crosslinked poly(styrene-co-divinylbenzene) microspheres by precipitation polymerization and their superior thermal properties, *J. Polym. Sci., Part A: Polym. Chem.* 42 (2004) 835–845.
- [24] S.M. Andonova, G.S. Şentürk, E. Kayhan, E. Ozensoy, Nature of the Ti–Ba interactions on the BaO/TiO₂/Al₂O₃ NO_x storage system, *J. Phys. Chem. C* 113 (2009) 11014–11026.
- [25] S.M. Andonova, G.S. Şentürk, E. Kayhan, E. Ozensoy, Fine-tuning the dispersion and the mobility of BaO domains on NO_x storage materials via TiO₂ anchoring sites, *J. Phys. Chem. C* 114 (2010) 17003–17016.
- [26] G.S. Şentürk, E.I. Vovk, V.I. Zaikovskii, Z. Say, A.M. Soyul, V.I. Bukhtiyarov, E. Ozensoy, SO_x uptake and release properties of TiO₂/Al₂O₃ and BaO/TiO₂/Al₂O₃ mixed oxide systems as NO_x storage materials, *Catal. Today* 184 (2012) 54–71.
- [27] T. Giannakopoulou, N. Todorova, G. Romanos, T. Vaimakis, R. Dillert, D. Bahnemann, C. Trapalis, Composite hydroxyapatite/TiO₂ materials for photocatalytic oxidation of NO_x, *Mat. Sci. Eng. B* 177 (2012) 1046–1052.
- [28] A. Mitsionis, T. Vaimakis, C. Trapalis, N. Todorova, D. Bahnemann, R. Dillert, Hydroxyapatite/titanium dioxidenanocomposites for controlled photocatalytic NO oxidation, *Appl. Catal., B: Environ.* 106 (2011) 398–404.
- [29] Y. Lin, Y. Tseng, J. Huang, C.C. Chao, C. Chen, I. Wang, Photocatalytic activity for degradation of nitrogen oxides over visible light responsive titania-based photocatalysts, *Environ. Sci. Technol.* 40 (2006) 1616–1621.
- [30] Y. Tseng, C. Kuo, C. Huang, Y. Li, P. Chou, C. Cheng, M. Wong, Visible-light-responsive nano-TiO₂ with mixed crystal lattice and its photocatalytic activity, *Nanotechnology* 17 (2006) 2490–2497.
- [31] N. Negishi, K. Takeuchi, T. Ibusuki, Surface structure of the TiO₂ thin film photocatalyst, *J. Mater. Sci.* 33 (1998) 5789–5794.
- [32] T. Sano, N. Negishi, K. Koike, K. Takeuchi, S. Matsuzawa, Preparation of visible-light-responsive photocatalyst from complex of Ti₄⁺ with nitrogen-containing ligand, *J. Mater. Chem.* 14 (2004) 380–384.
- [33] R. Hummatov, O. Gülseren, E. Ozensoy, D. Toffoli, H. Üstünel, First-principles investigation of NO_x and SO_x adsorption on anatase-supported BaO and Pt overlayers, *J. Phys. Chem. C* 116 (2012) 6191–6199.
- [34] O. Carp, C.L. Huisman, A. Reller, Photoinduced reactivity of titanium dioxide, *Prog. Solid State Chem.* 32 (2004) 33–177.
- [35] R.A. Spurr, H. Myers, Quantitative analysis of anatase-rutile mixtures with an X-ray diffractometer, *Anal. Chem.* 29 (1957) 760–762.
- [36] J. Lu, P. Zhang, A. Li, F. Su, T. Whang, Y. Liu, J. Gong, Mesoporous anatase TiO₂ nanocups with plasmonic metal decoration for highly active visible-light photocatalysis, *Chem. Commun.* 49 (2013) 5817–5819.
- [37] D.A. Erdogan, M. Polat, E. Ozensoy, (in preparation).